

# BOWSER-MORNER, INC.

Delivery Address: 4518 Taylorsville Road, Dayton, Ohio 45424 Mailing Address: P.O. Box 51, Dayton, Ohio 45401

AASHTO/ISO 17025 Accredited - USACE Validated



## REPORT ON TESTS OF CONCRETE CYLINDERS

**Report To:** Abilities First  
Attn: Jonathan Petefish  
1370 E. Primrose St.  
Springfield, MO 65804

**Report Date:** 6/22/18  
**Job No.:** 185302  
**Report No.:** 601278  
**No. of Pages:** 1

**Report On:** Density of Structural Lightweight Concrete (ASTM C 567)

**Sample ID:** Lightweight Concrete

ASTM C 567 - Density of Lightweight Concrete			
Specimen Number:	3A	3B	3C
Fresh Density, pcf:	unknown	unknown	unknown
Mass Suspended, g.	40.8	56.1	33.4
Mass SSD, g.	1738.3	1770.8	1666.2
Mass at Equilibrium, g.	1337.2	1344.8	1303.5
Oven Dried Density, pcf:	49.1	48.9	49.7
Avg. Oven Dried Density, pcf:	49.2		

Should you have any questions, or if we may be of further service, please contact me at (937) 236-8805 extension 322.

KAF/kaf  
601278  
1-File  
1-jpetefish@abilitiesfirst.net

Respectfully submitted,  
BOWSER-MORNER, INC.

Karl A. Fletcher, Manager  
Construction Materials and  
Geotechnical Laboratories